

OEM–approved

EFTEC, as a member of EMS-Chemie Holding is closely affiliated with leading car manufacturers around the world. We have supplied different chemical products to car manufacturers for decades, in the fields of bonding, sealing, cavity protection, underbody coating, antifleter, acoustic damping, etc.

Our chemists and engineers work closely together with the colleagues at the car manufacturer in order to improve today's products and systems as well as developing new solutions for the future.

We are partnering with the car manufacturers from the early stages in the development process of a new model all the way until its completion.

Our aftermarket products are not only OEM-approved, they are OEM.

The car manufacturers trust our products, so can

DINITROL URETHANE SELECTION CHART				
Product Name	Uses	Drive Away Time With airbags	Drive Away Time With out airbag	Lap Shear Strength At full cure
D-410	For rubber gasket sets, trims, moldings, and backfill.	—	—	260 PSI
D-500	Cost effective, great decking	6 hours	2 hours	910 PSI
D-500MV	Offers great cost , medium viscosity	6 hours	2 hours	910 PSI
D-500SA	Offers good decking and has super adhesion properties	6 hours	2 hours	880 PSI
D-501HV	High viscosity, standard modulus	3 hours	1 hour	1100 PSI
D-501HVHM	High viscosity, high modulus	2.5 hours	1 hour	1300 PSI
D-506	Heated product for all weather applications. Superior decking, high modulus	1.5 hours	1 hour	1070 PSI
D-9000	Cold applied, non-conductive, high modulus urethane	1 hour	45 minutes	910 PSI

* Drive away times listed are based at 73°F, 50% RH and may vary at other temperatures and humidity levels.

Revised September 2004

